



Family
Grout

Type

Fluid cement-based or hydraulic lime based grouts and micro mortars

Product Lines

- **Infratech**
- **Opus**

Functional Categories

- **Structural strengthening of masonry in historic buildings**
- **Roads and municipal maintenance interventions**
- **Structural maintenance of tunnels**

Components

Single-component

Appearance

Powder

GRT.0073

GROUT CABLE

Superfluid, reinforcing,
injectable cement grout

Customs Code

3816 0000

Dosage

1550 kg /m³

Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

Application

- Pour out
- Injection

General description

Superfluid, injectable, ultra-high flowability and stability cement grout, moderately expansive in the plastic phase, for fixings, anchorages, wall reinforcements, fillings, post-tensioning sheathing fills etc., based on high-resistance cements, specific agents, superpozzolanic reactive fillers. EXEMPT FROM FEES

General features

The mixing water requirement of GROUT CABLE, extremely reduced, is close to the permanently, chemically and physically set quantity, from the cement (stoichiometric water); there ensue exceptional characteristics in terms of stability and performance that are further increased by a peculiar anti-shrinkage action in the plastic phase and from the superpozzolanic reactivity that distinguishes the product.

Fields of application

Reinforcing and anchoring injections in galleries, hydraulic, industrial, marine, underground works; filling of containment sheaths, post-tensioned cable structures, padding, fissured concrete or mixed masonry works.


Available colours

- Gray

Basic features


 Mix with water:
28-30 %

 Nonflammable

 Pot-life:
30-45 min

 Shelf-life:
12 months

 Solvent-free

 Temperature of use:
+5/+35 °C

 UV-resistant

Technical specifications

Assenza di bleeding secondo UNI 8998

Compressive strength (UNI EN 1015-11): > 50 N/mm²

Darcy impermeability: 10[^](-10) cm/s

Flexural strength (UNI EN 1015-11): > 7 N/mm²

pH: >12 _

Water/binder ratio: 0.3 _

Tools cleansing

- Water

Applicable on

- Concrete
- Prefabricated concrete
- Mixed walls (bricks and stones)
- Stone walls

IF YOU WANT TO SOLVE IT


www.azichem.com

Updated: **31/01/2018**

General sales conditions and legal notices on

www.azichem.com/disclaimer

Instructions for use

Pour about 2/3 of the mixing water into the mixer, gradually add GROUT CABLE and the remaining water until a fluid and homogeneous mixture is obtained. Reinforcing backfills and fills can be carried out both by gravity and using manual or automatic pumps, depending on the type of application.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Warnings, Precautions and Ecology

Technical and performance data outlined in this document are the result of laboratory testing conducted in a conditioned environment, as such they can result as considerably changed from operating and application conditions. The need follows to carry out preliminary tests in actual use conditions.

The user is required to check the product's most recent Material Safety Data Sheet, reporting physical-chemical and toxicological data, risk phrases and other useful information on how to safely transport, use and dispose of the product and its packaging. It is also reminded that the product and its packaging must not be dispersed in the environment for any reason.

It is not advisable to use the product for reinforcing injections of vintage masonry made before 1900, since the risk of undesirable reactions with some internal masonry components (gypsum minerals) would cause the formation of "ettringite" and "thaumasite", deleterious for reinforcement as they are strongly expansive. In these cases, use SANAFUENS or FLUID CABLE added to hydraulic lime as an alternative.

GROUT CABLE is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **31/01/2018**
General sales conditions and legal notices on
www.azichem.com/disclaimer