



Family
Intotech

Type
Anchoring scratch coats

Product Lines
• **Building**
• **Opus**
• **Sanageb**

Functional Categories
• **Masonry plastering with plasters and skims**
• **Renewal of wet masonry with waterproofing plasters**
• **Thermal-insulating renewal of masonry**

Components
Single-component

Appearance
Powder

INT.0201

UNTERSANA

Breathable, dehumidifying
scratch coat, based on hydraulic
lime

Dosage

4 - 6 kg /m²
(Recommended: 5 kg /m²)

Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

Application

- Brick trowel
- Finishing trowel
- Plastering machine

Certifications and legislations



EN 998-1

Specification for Mortar for Masonry - Mortars for renovations (R)



Sanageb - Prodotti naturali per la Bioedilizia

Product belonging to Sanageb, Azichem's product line dedicated to green-building, sustainability in constructions and bio-architecture since 1994.

General description

Dehumidifying adhesive compound for the construction of anchoring scratch coats, for the subsequent application of normal plaster (INTOSANA), dehumidifying (SANATIGH) and light (SANAWARME and CAEOSANA), for new buildings, in existing buildings, for ecological building interventions and in the restoration of vintage buildings and monuments.

General features

UNTERSANA is composed of hydraulic lime, botticino, kaolin, calcium caseinate, Vichy salt, tartaric acid and natural fibres. Does not contain cements, resins, solvents, thinners and radioemissive aggregates.









Fields of application

Anchoring scratch coat (applied by "spraying" or "splashing") for the formation of an adhesive bridge for easy grip of subsequent plasters, dehumidifying, breathable, based on hydraulic lime.

Available colours

• Light gray

Basic features

 Maximum diameter of aggregate: 1.5 mm	 Min. recommended thickness: 4 mm
 Mix with water: 20-22 %	 Nonflammable
 Pot-life: 60 min	 Shelf-life: 12 months
 Solvent-free	 Temperature of use: +5 / +30 °C

Technical specifications

Bonding force (UNI EN 1015-12): 2.42 N/mm²

Breathability (UNI EN 1015-19): 14 μ

Capillary absorption (UNI EN 1015-18): 0.48 kg•h^{0.5}/m²

Complete hardening (a 20°C): 3 day

Compressive strength (UNI EN 1015-11): > 26 N/mm²

Density (UNI EN 1015-6): 1850 kg/m³

Flexural strength (UNI EN 1015-11): > 4 N/mm²

Reaction to fire (EN 13501-1): A1 _

Static elastic modulus (EN 13412): 11500 N/mm²

IF YOU WANT TO SOLVE IT


www.azichem.com

Updated: **24/02/2018**

General sales conditions and legal
notices on

www.azichem.com/disclaimer

Page: **1/3**

Tools cleansing

- Water

Applicable on

- Bricks
- Mixed walls (bricks and stones)
- Brickworks
- Stone walls

Substrate preparation

Application surfaces should be clean, free of soiling, crumbling and non-adhering parts, dust, etc., conveniently saturated with water until they reach the condition "saturated with dry surface".

Instructions for use

Pour about 2/3 of the mixing water into the mixer, add UNTERSANA and the remaining water; continue to mix until a homogeneous lump-free mixture is obtained. The mixing water should be about 16-18% of the weight of the bag. After mixing is completed wait a few minutes before applying.

"Spray" the product, with plastic fluid consistency, on the application supports, with plastering trowel and brick trowel or with plastering pump. Protect fresh surfaces from direct exposure to sunlight, from the rain and wind, cure the prolonged moist hardening.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Warnings, Precautions and Ecology

Technical and performance data outlined in this document are the result of laboratory testing conducted in a conditioned environment, as such they can result as considerably changed from operating and application conditions. The need follows to carry out preliminary tests in actual use conditions.

The user is required to check the product's most recent Material Safety Data Sheet, reporting physical-chemical and toxicological data, risk phrases and other useful information on how to safely transport, use and dispose of the product and its packaging. It is also reminded that the product and its packaging must not be dispersed in the environment for any reason.

For a proper adhesion of the next plaster, it is appropriate to apply the latter before the complete curing of the rendering UNTERSANA (within 24-36 hours).



www.azichem.com

Updated: **24/02/2018**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

UNTERSANA is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **24/02/2018**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Page: **3/3**