



GRT.0067

GROUT 2

Rheoplastic, structural, anti-shrinkage mortar, for precision anchorage

Customs Code

3824 5090

Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

Application

- Pour out

Family
Grout

Product Lines
• **Infratech**

Components
Single-component

Type
Structural free-flowing cement mortars

Functional Categories
• **Block repair of concrete works with free-flowing mortars**
• **Construction and maintenance interventions on airport runways and quays**
• **Roads and municipal maintenance interventions**
• **Structural maintenance of bridges and viaducts**
• **Structural precision anchoring**

Appearance
Powder

Certifications and legislations



EN 1504-6

Products and systems for the protection and repair of concrete structures - Anchoring of reinforcing steel bar



EN 1504-3

Products and systems for the protection and repair of concrete structures - Structural and non-structural repair (R4)

General description

GROUT 2 is a very high performance pourable mortar, fiber-reinforced with READYMESH polypropylene microfibres, used for anchoring and structural reintegration on reinforced concrete, with durability, adhesion to the substrate, mechanical resistance to compression and flexion much higher than normal structural concrete.

General features

GROUT 2 is self-leveling, perfectly pourable, with a maximum aggregate size of 2 mm, and is able to completely fill the most tortuous cavities, normally inaccessible, even if far from the casting point and with a very narrow air gap. The high content of microsilic with pozzolanic activity and the absence of "bleeding", help to generate a very strong adhesion to the substrate and to the foundation or reinforcement iron. Other features are the elimination of plastic shrinkage, the compensation of hygrometric shrinkage, excellent durability to chemical attacks, freeze and thaw cycles, resistance to fats and oils.

The exceptional ANTI-CORROSIVE and PROTECTIVE capacity ON REINFORCEMENTS is achieved thanks to the following properties:

- the mix of highly resistant superfine binders, combined with very fine silicas with pozzolanic activity, makes the mortars, at the end of the hardening process, intrinsically impermeable to water;
- the strongly alkaline pH (> 12) protects the reinforcing rods from the initiation of corrosion;
- the negligible breathability to carbon dioxide gives the hardened mortars very high anti-carbonation characteristics.

The combination of these anticorrosive specificities makes the classic passivation treatment of reinforcing bars, preparatory to the casting of the pourable mortar, NOT NECESSARY, provided that, between the white metal cleaning operations and the castings of the pourable mortar, it does not elapse too long. time, with the risk of a new start of oxidative processes. Therefore, only if long exposure times are foreseen between the cleaning operations of the iron and the castings of the pourable mortar, it is advisable to treat with passivating grout (REPAR MONOSTEEL or REPAR STEEL), applied with a brush and localized only on d 'armor. For the construction of road joints, in works with high vehicle traffic, it is possible to add GROUT 2 with 25 kg / m³ (300 gr / 25 kg bag) of READYMESH MM-150 steel fibers and 1 kg / m³ (10 gr / bag) of READYMESH PM-060 polypropylene fibers.

Dosage

Approximately 19 kg/m² of GROUT 2 for every centimetre of thickness to be implemented (approximately 1900 kg per cubic metre).



www.azichem.com

Updated: **07/12/2020**










General sales conditions and legal notices on

www.azichem.com/disclaimer

Fields of application

Precision anchorage of operating machines: presses, turbines, power supplies, rolling mills, alternators, bridge cranes, metal structures, tracks, etc. Structural adjustments, restorations, drawing and armouring, through injections or castings poured in caisson. Realisation of connecting anchorages through steel bars with diameter and depth consistent with design specifications, through casting in perforations provided for this purpose. Construction of structural road joints.

Basic features

 Max. recommended thickness: 15 cm	 Maximum diameter of aggregate: 2 mm
 Min. recommended thickness: 2 cm	 Mix with water: 14 %
 Pot-life: 30 min	 Shelf-life: 12 months
 Temperature of use: +5 / +35 °C	 UV-resistant
 Available colours Gray	

Technical specifications

<i>Bonding force (UNI EN 1015-12):</i> 2.32 N/mm ²
<i>Capillary absorption (UNI EN 13057):</i> 0.45 kg•h ^{0.5} /m ²
<i>Chloride content (EN 1015-17):</i> < 0.01 %
<i>Compressive strength (EN 12190):</i> > 75 N/mm ²
<i>Darcy impermeability:</i> 10 ⁻¹⁰ cm/s
<i>Density (UNI EN 1015-6):</i> 2100 kg/m ³
<i>Determination of thermal compatibility (EN 13687-1 - A/B):</i> 2.0 N/mm ²
<i>Flexural strength (EN 12190):</i> > 10 N/mm ²
<i>Reaction to fire (EN 13501-1):</i> A1 _
<i>Resistance to carbonatation (EN 13529):</i> 1 mm
<i>Resistance to lubricating oils (oil bath for 60 days at 40°C):</i> NO DEGRADES
<i>Skid resistance (EN 13036-4 - CS III):</i> 68 mm
<i>Static elastic modulus (EN 13412):</i> 30000 N/mm ²
<i>Water/binder ratio:</i> 0.35 _

Tools cleansing

- Water

Applicable on

- Concrete
- Prefabricated concrete
- Mixed walls (bricks and stones)
- Rusty reinforcement rods

Substrate preparation

Application surfaces should be clean, free of soiling, crumbling and non-adhering parts, dust, etc., conveniently saturated with water until they reach the condition "saturated with dry surface".

Instructions for use

Insert 2/3 (approximately 2.5 litres per bag) of the total mixing water in the cement mixer, then gradually add the product and the remaining water, mix until a homogeneous lump-free mixture of the desired consistency is obtained.

For high anchoring sections GHIAIETTO 6.10 should be added (please refer to the appropriate technical data sheet for more information).



www.azichem.com

Updated: **07/12/2020**
General sales conditions and legal notices on
www.azichem.com/disclaimer

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Additional adhesion parametres

- Adhesion to smooth iron: $>4.5 \text{ N/mm}^2$
- Adhesion to iron with improved adherence : $>35 \text{ N/mm}^2$

Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

Given the self-levelling properties of the product and its self-compacting properties, it is recommended to pay special attention to the vibration step. A excessive zeal in the vibration operation can worsen the aesthetic appearance of the resulting product.

Do not use in the absence of adequate lateral confinement.

Cure the protection and the moist hardening of exposed surfaces.

Adopt casting procedures capable of ensuring the absence of gaps and discontinuities, pouring the mortar from a single part of the casting perimetre to avoid air pockets.



www.azichem.com

Updated: **07/12/2020**
General sales conditions and legal notices on www.azichem.com/disclaimer

GROUT 2 is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **07/12/2020**
General sales conditions and legal
notices on
www.azichem.com/disclaimer