



GRT.0070

GROUT 6

Castable, rheoplastic, structural, controlled shrinkage grout mortar

Customs Code

3824 5090

Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

Application

- Pour out

Family
Grout

Product Lines

- Building
- Infratech

Components
Single-component

Type
Structural free-flowing cement mortars

Functional Categories

- Block repair of concrete works with free-flowing mortars
- Roads and municipal maintenance interventions
- Structural maintenance of dams, reservoirs, ducts and water ducts
- Structural maintenance of bridges and viaducts
- Structural maintenance of tunnels
- Structural precision anchoring

Appearance
Powder

Certifications and legislations



EN 1504-6

Products and systems for the protection and repair of concrete structures - Anchoring of reinforcing steel bar



EN 1504-3

Products and systems for the protection and repair of concrete structures - Structural and non-structural repair (R4)

General description

Rheoplastic controlled shrinkage cement screed, with superfluid consistency, based on high-resistance cements, polymeric modifiers, shrinkage resistant agents, anti-allergic additives, selected siliceous aggregates.

Dosage

Approximately 19,50 kg/m² of GROUT 6 for every centimetre of thickness to be implemented (approximately 1950 kg per cubic metre).

Fields of application

Structural restoration, dimensional adjustments, reinforcements, high dimension anchorages, drawing and armouring works, etc., by pumped or poured casting installation. Realisation of structural road joints.

Basic features

- | | |
|--|---|
|  Max. recommended thickness:
30 cm |  Maximum diameter of aggregate:
6 mm |
|  Min. recommended thickness:
1(*) - 4 cm |  Mix with water:
10-12 % |
|  Pot-life:
60 min |  Shelf-life:
12 months |
|  Temperature of use:
+5 / +35 °C |  Available colours
Gray |

Technical specifications

Bonding force (UNI EN 1542): ≥ 2 N/mm²

Capillary absorption (UNI EN 13057): 0.49 kg•h^{0.5}/m²

Chloride content (UNI EN 1015-17): < 0.01 %

Compressive strength (UNI EN 1015-11): > 70 N/mm²

Concrete adhesion (cutting test): > 5 MPa

Density (UNI EN 1015-6): 2190 kg/m³

Determination of thermal compatibility (UNI EN 13687-1): ≥ 2 mPa

IF YOU WANT TO SOLVE IT


www.azichem.com

Updated: 10/06/2021

General sales conditions and legal notices on

www.azichem.com/disclaimer

Flexural strength (UNI EN 1015-11): > 8 N/mm²

Reaction to fire (EN 13501-1): A1 _

Resistance to carbonatation (UNI EN 13295): 0.5 mm

Resistance to the extraction of the steel bars with improved
adhesion: > 30 MPa

Skid resistance (UNI EN 13036-4): 50 mm

Static elastic modulus (EN 13412): 30000 N/mm²

Tools cleansing

- Water

Applicable on

- Concrete
- Prefabricated concrete
- Mixed walls (bricks and stones)
- Rusty reinforcement rods

Substrate preparation

Application surfaces should be clean, free of soiling, crumbling and non-adhering parts, dust, etc., conveniently saturated with water until they reach the condition "saturated with dry surface".

Instructions for use

Insert 2/3 (approximately 2.5 litres per bag) of the total mixing water in the cement mixer, then gradually add the product and the remaining water, mix until a homogeneous lump-free mixture of the desired consistency is obtained.

For high anchoring sections GHIAIETTO 6.10 should be added (please refer to the appropriate technical data sheet for more information).

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



www.azichem.com

Updated: **10/06/2021**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

Given the self-levelling properties of the product and its self-compacting properties, it is recommended to pay special attention to the vibration step. A excessive zeal in the vibration operation can worsen the aesthetic appearance of the resulting product.

Do not use in the absence of adequate lateral confinement.

Cure the protection and the moist hardening of exposed surfaces.

Adopt casting procedures capable of ensuring the absence of gaps and discontinuities, pouring the mortar from a single part of the casting perimetre to avoid air pockets.

GROUT 6 is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **10/06/2021**
General sales conditions and legal
notices on
www.azichem.com/disclaimer