



GRT.0262

## GROUT 2 SFR

Rheoplastic, shrink-proof, fibre-reinforced mortar for precision anchorage

### Customs Code

3824 5090

### Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

### Application

- Pour out

Family  
**Grout**

Product Lines  
• **Infratech**

Components  
**Single-component**

Type  
**Structural free-flowing cement mortars**

Functional Categories  
• **Block repair of concrete works with free-flowing mortars**  
• **Construction and maintenance interventions on airport runways and quays**  
• **Roads and municipal maintenance interventions**  
• **Structural maintenance of bridges and viaducts**  
• **Structural precision anchoring**

Appearance  
**Powder**

## General description

Shrink-proof, rheoplastic, pouring mortar for precision anchorage of operating machines, turbines, rolling mills, overhead cranes, etc.. With a cement binding base, super-lubricating agent, shrink-proof compounds, select aggregates, fibre-reinforced with a mix of steel and polypropylene fibres and super-pozzolanic reactive fillers.

## Fields of application


Precision anchorage of operating machines: presses, turbines, power supply units, rolling mills, alternators, overhead cranes, metal structures, tracks, etc.. Structural adaptation, renovations, drawing and reinforcements, using injections and castings inside formworks. Creation of connection anchorage using steel bars with a diameter and depth consistent with the project specifications, by casting in specifically prepared perforations. Construction of structural road joints.

## Basic features


 Density:  
2.200 kg/dm<sup>3</sup>

 Max. recommended thickness:  
15 cm


 Maximum diameter of aggregate:  
2 mm


 Mix with water:  
15 %

 Nonflammable

 Pot-life:  
30 min

 Shelf-life:  
12 months

 Temperature of use:  
+5 / +35 °C

 Available colours  
Gray

## Technical specifications

*Bonding force (UNI EN 1542): 2.4 MPa*

*Compressive strength (UNI EN 1015-11): 70.03 N/mm<sup>2</sup>*

*Flexural strength (UNI EN 1015-11): 10.3 N/mm<sup>2</sup>*

*Reaction to fire (EN 13501-1): A1 \_*

## Tools cleansing

- Water

## Applicable on

- Concrete
- Prefabricated concrete
- Mixed walls (bricks and stones)
- Rusty reinforcement rods

## Instructions for use

Place 2/3 (approx 2.5 litres per bag) of the total water in the mix, then gradually add the product and the remaining water, mixing until you obtain an even mix with the desired consistency and no lumps.



[www.azichem.com](http://www.azichem.com)

Updated: **24/08/2020**

General sales conditions and legal notices on

[www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)

## Substrate preparation

The application surfaces should be clean, free of containment, inconsistent and incoherent parts, dust, etc., conveniently saturated with water to reach the "saturated to dry surface" condition.

## Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



## Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: [www.azichem.com](http://www.azichem.com). The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: [www.azichem.com](http://www.azichem.com).

It is forbidden to dispose of the product and/or packaging in the environment.

Given the self-levelling properties of the product and its self-compacting capacity, you are advised to pay due attention to the vibration phase. Excess zeal in the vibration operation could worsen the aesthetic performance of the resulting manufactured work.

Do not use in the absence of adequate side confinements.

Ensure protection and damp seasoning of the surfaces exposed.

Implement casting procedures capable of ensuring the absence of vacuums and cracks; grout the mortar from one part of the perimeter of the casting to avoid air sacks.



[www.azichem.com](http://www.azichem.com)

Updated: **24/08/2020**  
General sales conditions and legal notices on [www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)

*GROUT 2 SFR is produced/distributed by*



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy  
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



[www.azichem.com](http://www.azichem.com)

Updated: **24/08/2020**  
General sales conditions and legal  
notices on  
[www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)

Page: **3/3**