



PRS.0242

CLAYSEAL 25.20 SW

Bentonite-rubber swelling joint,
specific for usage with sea water

Customs Code

4006 9000

Packaging

- Box: 6 x (Roll 5 m)
- Pallet: 48 x (Box 21 Kg)

Application

- Apply by hand
- Hammer

Family
Proseal

Product Lines

- Aqua
- Infratech
- Sanageb

Type

Sodium bentonite based hydro expansive products

Functional Categories

- **Waterproofing underground structures with hydro-expansive products**
- **Construction and maintenance interventions on airport runways and quays**
- **Structural maintenance of dams, reservoirs, ducts and water ducts**
- **Structural maintenance of tunnels**
- **Construction of underground works in high performance waterproof concrete**

Components

Single-component

Appearance

Stripe

General description

High performance hydro-expansive sealing waterstop for construction joints with safe hermetic seal for structures, masonry and foundations, made of a mixture of sodium bentonite, hydro-expansive rubber and special binding polymers ("hydrocarbon"), specifically designed to be used in contact with salt water or organic leachates. CLAYSEAL 25.20 SW has a rectangular cross section of 25x20 mm, packed in rolls of 5 m each.

General features

CLAYSEAL 25.20 SW is a simple and easy to apply sodium bentonite waterstop; it does not require any special preparations of the media, pre-shaped seats etc. It is easily fixed by nailing and does not require any special protection. In contact with water (even salted or polluted), it increases its volume through the formation of a stable colloidal system that guarantees the permanent hermetic sealing of the connection; the initial expansion is delayed through a retardant coating with respect to the first contact with water, to avoid deformations in the initial hardening phase of the fresh concrete.

The expansion of CLAYSEAL 25.20 SW in salt water or water with leachate and pollutant content, is at least 180% (just under twice its initial volume). Potential expansion in case of contact with clean water could be significantly higher (even of the order of 1000%).


Dosage

1.1 m/m: Use 1 metre of CLAYSEAL 25.20 SW for each linear metre, being careful to place 5-10 cm of the product alongside the end/start roll points to guarantee the permanent water tightness of the system.

Fields of application


Producing rigid construction joints (non-expanding) and safely and permanently hydraulic sealing connections in environments with salt water, sea water, organic leachate and pollutants of various kinds (for example landfills, biogas digesters, etc.).


Basic features

 Density:
1.4-1.5 kg/dm³

 Hydroexpansive product:
>180 %

 Shelf-life:
12 months

 Temperature of use:
-15 / +50 °C

 Available colours
Red

Technical specifications

Longitudinal elongation at break: 60 %

Sodium bentonite content: >75 %

Unit weight (ASTM D71): 0.83 kg/m

IF YOU WANT TO SOLVE IT


www.azichem.com

Updated: **24/08/2020**

General sales conditions and legal notices on

www.azichem.com/disclaimer

Substrate preparation

Prepare the smoothest and most planar laying surface, using REPAR TIX to compensate for any inhomogeneity, and accurately remove crumbling, non-adhering, powdery parts.

Instructions for use

Apply by hand the waterstop in sodium bentonite CLAYSEAL 25.20 SW in the provided position. The product should be secured with nails: a steel nail and a washer about every 20-25 cm. The sealing of joints between the waterstop beads is ensured by the simple approach of at least 10 cm and not by overlapping the ends.

For particularly complex applications, is available the specific cage of steel wire BENTONET, with square mesh of 13x13 mm, in profiles of 1 meter each.

The positioning must ensure a concrete covering of 10-12 cm in order to contain the expansive action generated by hydration.


Although the product has a delayed expansion of 48h, it is not recommended for use in cases of earlier time-frames or with excessive humidity (for example in the presence of puddles).

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Comparison of expansion with CLAYSEAL 25.20



Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

CLAYSEAL25.20 SW is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **24/08/2020**
General sales conditions and legal
notices on
www.azichem.com/disclaimer