



SYN.0106

SYNTECH PAVISHEER

Epoxy treatment for transparent coatings

Customs Code

3907 3000

Packaging

- Can 10 kg [A]
- Can 5 kg [A]
- Canister 1 kg [A]
- Can 10 kg [B]
- Can 5 kg [B]
- Canister 1 kg [B]
- Kit: 1 Canister 1 kg [A] + 1 Canister 1 kg [B]
- Kit: 1 Can 5 kg [A] + 1 Can 5 kg [B]
- Kit: 1 Can 10 kg [A] + 1 Can 10 kg [B]

Application

- Brush
- Paint roller

Family
Syntech

Product Lines
• Infratech
• Floor

Components
Two-components

Type
Epoxy and polyurethane primers, treatments and coatings

Functional Categories
• Construction of bonding bridges between the existing support and the new slope
• Wall structure treatments and repair of industrial concrete floors
• Protective, strengthening, polyurethane or epoxy coatings

Appearance
Liquid + Liquid

Certifications and legislations



EN 1504-2

Products and systems for the protection and repair of concrete structures - Surface protection systems for concrete

General description

A two-component epoxy system based on epoxy resins in aqueous dispersion and solvent-free. It is ideal for completing protective, transparent treatments with a consolidating action and anti-dust effect on industrial concrete flooring, with good mechanical and chemical resistance, especially in reference to contact with oils and solvents. This product also serves well as a primer for casting joints between old and new concrete flooring.

Fields of application

Transparent finish of interior floor coverings, mechanical-resistant impregnations, anti-dust and anti-oil for concrete surfaces.

Basic features



Density:
1.09 kg/l

A:B Mixing ratio:
1:1



Nonflammable



Pot-life:
80 -120 min



Shelf-life:
12 months



Solvent-free



Temperature of use:
+5 / +35 °C



Use wearing protective gloves



Available colours
Transparent

Technical specifications

Capillary absorption (UNI EN 1062-3): 0.02 kg/(m² • h^{0.5})

Complete hardening (a 20°C): 7 day

Hard to touch (a 20°C): 0.5 h

Viscosity (UNI EN ISO 3219): Comp A 14700 / Comp B
20500 mPa

Walkability: 24 h

IF YOU WANT TO SOLVE IT


www.azichem.com

Updated: 28/10/2021

General sales conditions and legal notices on

www.azichem.com/disclaimer

Page: 1/3

Tools cleansing

- Water

Applicable on

- Concrete
- Prefabricated concrete
- Tiles
- Floor screed
- Rock walls

Instructions for use

Mix components A and B each in their own container before mixing. Do not take partial quantities from the packs to avoid any errors in the mixing ratio that would cause failure or incomplete hardening. Pour component B into a suitable container and add component A. Mix everything for a few minutes using a mechanical stirrer with variable speed until a homogeneous and uniform color mixture is obtained. Leave to rest for a few minutes and mix again. Dilute the final product only with water in the SYNTECH PAVISHEER: water ratio of 1: 3 for the first coat and 1: 2 for the second. Gradually add the dilution water, continuing to mix for a few minutes. The dilution ratio can vary according to the porosity of the support; if necessary on closed surfaces it is also possible to dilute the second coat respecting the dilution ratio 1: 3. The SYNTECH PAVISHEER emulsion has a stability of about 2 hours at 20 ° C; within this period the product must be used. SYNTECH PAVISHEER is applied with a short-haired roller or spray, covering the entire surface evenly. We recommend application at temperatures not lower than 5 ° C.

Substrate preparation

The media should have adequate mechanical resistance. The concrete surfaces should be cured, dry, planar and absorbent, free from oils, detergents, powders and soiling. The most appropriate type of mechanical preparation should also be determined (degreasing or shot peening).

Conveniently absorbent surfaces may be dealt with directly after a proper cleaning. For tiled surfaces and for pre-existing coverings in resin, a degreasing or shot peening treatment is required until complete opacification and complete elimination of dust.

Storage and preservation

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Store the product at a temperature between +5°C and +35°C.



Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.



www.azichem.com

Updated: **28/10/2021**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

SYNTECH PAVISHEER is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **28/10/2021**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Page: **3/3**